

Experts in Rubber

Manufacturers · Designers · Distributors

Supersil Coated Glass Cloth Datasheet

Product Code: RC0382R-1.2

Product Description

Glass cloth undergoes a specialised treatment wherein it is coated with a robust, heavyweight silicone rubber known as Supersil. This silicone rubber is uniquely formulated with a high concentration of iron oxide, lending it a distinctive red colour. The presence of iron oxide is crucial as it serves two significant purposes: it enhances the silicone's temperature tolerance and enables the material to withstand brief exposure with molten metal.



Technical Specification

Finished Coated Fabric	Units	Value	Tolerance
Weight	g/m²	1450	±5%
Thickness	mm	1.2	±5%
Standard Useable Width	mm	1500	±5%
Standard Roll Length	m	50	
Maximum Operating Temperature	Maximum continuous operating temperature is 250°C. Base fabric will withstand 550°C (unstressed).		
Colour / Description	Red silicone coating one side, white glass fibres on the other side.		

Base Fabric Construction	Units	Value	Tolerance
Weight	g/m²	1050	±5%
Weave Pattern	Cross Twill		
Construction: Warp Weft	per cm per cm	16 7.2	±5% ±5%
Yarn Count: Warp Weft	TEX TEX	EC9 136/3 EC9 136/3	





The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.



Experts in Rubber

Manufacturers · Designers · Distributors

Base Fabric Construction	Units	Value	Tolerance
Tensile Strength			
Warp	N / 5cm	8700	±10%
Weft	N / 5cm	4000	±10%

Base Fabric Construction	Units	Value	Tolerance	
Weight	g/m²	400	±10%	
400 g/m2 of red silicone on one side.				





The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.